



PRODUCT DATA SHEET

SUPABOARD ADHESIVE

High Strength Panel Adhesive Membrane

SUPABOARD ADHESIVE is a high strength water based panel adhesive membrane suitable for bonding fibre cement, calcium silicate and magnesium oxide boards to foam panels. Supaboard Adhesive is designed to provide maximum bonding adhesion for many other substrates with the added benefit of being water based and solvent free. Supplied in easy to use 600ml sausages for electric or manual mastic dispensers.

Physical Characteristics

Product type	Solvent-free dispersion of modified acrylic resins with mineral fillers and lightfast pigments
Appearance	Viscous white liquid.
Viscosity@25°C	7,000 – 8,000 mPa
Density @ 25°C	1.14 Kg/Lt
Solids	Approximately 55%
Application Rate	600ml sausage will generally cover 9 Lineal meters for 8mm wide by 8mm thick W.F.T.
Film Formation	Temperatures above +5°C
Susceptibility to Frost	Avoid freezing conditions. Store above +2°C
Storage Stability	2 Years or more in suitable conditions (18°C to 50 °C)
Cleaning Agent	Water
Danger Classification	Not Applicable. Non Hazardous.

Application Information

Surface Preparation	Surface must be clean, stable and free of oil and grease. Loose particles should be removed and repairs carried out if required.
Application Conditions	Not to be applied in temperatures below +5 °C or during rain. High humidity and low temperatures will affect cure time.
Application Process	Apply via electric or manual mastic dispensers.

Application Information - continued

Drying

Setting time 5 to 6 hours. Curing time 8 to 10 hours. Based on recommended volumes, application method and applied weight. Thickness of applied film, air temperature, humidity, air circulation and applied pressure can vary the setting and curing time of the product.

Equipment Cleanup:

Wash all equipment thoroughly with water.

Safety Precautions:

Avoid ingestion and contact with skin or eyes. Wear protective goggles and waterproof gloves.

Pack Sizes:

600ml sausages

Contact Point

For further information and technical assistance please contact:

Uniseal Manufacturing
17 Ryelane Street
Maddington WA 6109
Tel: 1300 577 719
Fax: 1300 366 353
Email: uniseal@sealingservices.com.au
www.unisealcoatings.com.au



Uniseal Manufacturing is a division
of the Global Group of Companies

DISCLAIMER: Please note that this information is supplied based on field and laboratory tests and is, to the best of our knowledge, deemed to be correct, however, no guarantee of the accuracy of this information in all instances is intended or implied and Uniseal Manufacturing accepts no liability for any failure or loss that may result from the application process. Please contact Uniseal Manufacturing if additional or task-specific information is required.